

[illegible]

The simple view that glass formation is the explanation for stability is incomplete. This explanation only holds for glasses that are inherently chemically unreactive and stable. It is incontrovertible that certain substances that form physically excellent glasses are nevertheless very poor stabilisers. Many of these are either chemically reactive, such as reducing sugars or are unstable, like sucrose or sorbitol and break down to reactive intermediates which degrade the product during storage in the dry state (Newman Y.M., Ring S.G. and Colaco C. The role of trehalose and other carbohydrates in biopreservation. *Biotechnol. & Genet. Eng. Rev.* 11 263-294 (1993)). A common reactivity of sugar glasses is the reducing action of the carbonyl group and the degradation products formed are often the familiar carbonyl-amine compounds of the Maillard reaction (Ellis G.P. The Maillard reaction. *Adv. Carbohydr. Chem.* 14 63-134 (1959)). Because the Maillard reaction is temperature dependent, it is only slowly progressive at low temperatures. Many glass-forming materials give excellent preservation of activity during the drying process

itself but the product subsequently undergoes progressive deterioration unless stored under refrigeration.

The error of ignoring the subtle sugar chemistry that can proceed in dried preparations is widespread in the literature and has led to the advocacy of simple tests of the glass transition temperature of pure sugar solutions as a means of selecting good stabilisers. This approach has actually led to the recommendation of quite useless substances in the past (Franks F. Freeze drying: From empiricism to predictability *Cryoletters* 11 93-110 (1990)). In fact, the efficacy of a formulation is the result of multiple physical and chemical interactions between all the components in the formulation, including the active, on drying. All these interactions may not be predicted by current theories.

The superiority of the disaccharide trehalose as a stabiliser was first indicated by its prevalence in certain rare living creatures, which regularly dried out and could come back to life on rehydration. (Crowe J.H., Crowe L.M. and Chapman D. Preservation of membranes in anhydrobiotic organisms: The role of trehalose. *Science* **223** 701 (1984)). In laboratory studies, trehalose incorporated into the buffer solutions from which active biomolecules were dried, resulted in a product with quite remarkable resistance to denaturation by heat (Colaco C.A.L.S., Sen S., Thangavelu M., Pinder S. and Roser B. Extraordinary stability of enzymes dried in trehalose: Simplified molecular biology. *Biotechnol.* **10**. 1007-1011 (1992)). Because it is subsequently degraded in the body by the specific enzyme, trehalase, to two molecules of glucose, trehalose possesses many of the properties of the ideal industrial stabiliser for foods and medical products. A large scientific and patent literature has now developed on trehalose stabilisation of foods, vaccines, diagnostics and drugs. The disadvantages of trehalose are that it is as yet not approved by the regulatory authorities, it is expensive and it contains contaminating reducing sugars, especially glucose, in all but the most rigorously purified material.

One of the alternative non-reducing and chemically stable sugar derivatives that might be expected to stabilise effectively is mannitol. Because of its remarkable resistance to water sorption at high atmospheric humidity (Wade A. and Weller P.J. Handbook of Pharmaceutical Excipients second edition p296 (1994)); it is widely used in tablet and powder formulations as a bulking and anti-caking agent. In combination with other excipients such as glycine, it is also widely used in freeze dried parenteral preparations but

	1970	1971	1972	1973	1974	1975	1976	1977	1978	1979	1980	1981	1982	1983	1984	1985	1986	1987	1988	1989	1990	1991	1992	1993	1994	1995	1996	1997	1998	1999	2000	2001	2002	2003	2004	2005	2006	2007	2008	2009	2010	2011	2012	2013	2014	2015	2016	2017	2018	2019	2020	2021	2022	2023	2024	2025	2026	2027	2028	2029	2030	2031	2032	2033	2034	2035	2036	2037	2038	2039	2040	2041	2042	2043	2044	2045	2046	2047	2048	2049	2050	2051	2052	2053	2054	2055	2056	2057	2058	2059	2060	2061	2062	2063	2064	2065	2066	2067	2068	2069	2070	2071	2072	2073	2074	2075	2076	2077	2078	2079	2080	2081	2082	2083	2084	2085	2086	2087	2088	2089	2090	2091	2092	2093	2094	2095	2096	2097	2098	2099	2100	2101	2102	2103	2104	2105	2106	2107	2108	2109	2110	2111	2112	2113	2114	2115	2116	2117	2118	2119	2120	2121	2122	2123	2124	2125	2126	2127	2128	2129	2130	2131	2132	2133	2134	2135	2136	2137	2138	2139	2140	2141	2142	2143	2144	2145	2146	2147	2148	2149	2150	2151	2152	2153	2154	2155	2156	2157	2158	2159	2160	2161	2162	2163	2164	2165	2166	2167	2168	2169	2170	2171	2172	2173	2174	2175	2176	2177	2178	2179	2180	2181	2182	2183	2184	2185	2186	2187	2188	2189	2190	2191	2192	2193	2194	2195	2196	2197	2198	2199	2200	2201	2202	2203	2204	2205	2206	2207	2208	2209	2210	2211	2212	2213	2214	2215	2216	2217	2218	2219	2220	2221	2222	2223	2224	2225	2226	2227	2228	2229	2230	2231	2232	2233	2234	2235	2236	2237	2238	2239	2240	2241	2242	2243	2244	2245	2246	2247	2248	2249	2250	2251	2252	2253	2254	2255	2256	2257	2258	2259	2260	2261	2262	2263	2264	2265	2266	2267	2268	2269	2270	2271	2272	2273	2274	2275	2276	2277	2278	2279	2280	2281	2282	2283	2284	2285	2286	2287	2288	2289	2290	2291	2292	2293	2294	2295	2296	2297	2298	2299	2300	2301	2302	2303	2304	2305	2306	2307	2308	2309	2310	2311	2312	2313	2314	2315	2316	2317	2318	2319	2320	2321	2322	2323	2324	2325	2326	2327	2328	2329	2330	2331	2332	2333	2334	2335	2336	2337	2338	2339	2340	2341	2342	2343	2344	2345	2346	2347	2348	2349	2350	2351	2352	2353	2354	2355	2356	2357	2358	2359	2360	2361	2362	2363	2364	2365	2366	2367	2368	2369	2370	2371	2372	2373	2374	2375	2376	2377	2378	2379	2380	2381	2382	2383	2384	2385	2386	2387	2388	2389	2390	2391	2392	2393	2394	2395	2396	2397	2398	2399	2400	2401	2402	2403	2404	2405	2406	2407	2408	2409	2410	2411	2412	2413	2414	2415	2416	2417	2418	2419	2420	2421	2422	2
--	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	---

is added as a carrier to produce a stiff, homogeneous cake that improves the appearance of the lyophilised plug in a vial (Wade & Weller The Excipients Handbook 1994).

In published surveys of the stabilising ability of a wide range of sugars and sugar derivatives (Colaco C.A.L.S., Smith C.J.S., Sen S., Roser B.J., Newman Y., Ring S. and Roser B.J. Chemistry of protein stabilisation by trehalose in *Formulation and delivery of proteins and peptides* Cleland and Langer eds American Chemical Society Washington 222-240 (1994)), it was shown that mannitol and sorbitol were very poor stabilisers. Indeed in several patent applications it has been claimed that mannitol and certain other monosaccharide alcohols cannot stabilise at all. PCT No WO 91/18091 "Stabilisation of biological macro-molecular substances and other organic compounds", Roser B.J. and Colaco C claimed that only non-reducing glycosides of a polyhydroxy sugar alcohol or other straight chain polyalcohol or raffinose, stachyose or melezitose were effective in achieving stability, especially on storage. This patent states "Thus the monosaccharide sugar alcohols galactitol, mannitol and erythritol are not satisfactory protective agents". US patent Number 5,621,094 "Method of Preserving Agarose Gel Structure During Dehydration by Adding a Non-reducing Glycoside of a Straight Chain Sugar Alcohol" by Roser B. and Colaco C states that "glucose mannitol and sorbitol failed after one week" while "lactitol and trehalose were perfect after >12 weeks". It further defined effective formulations as "wherein the non-reducing glycoside of a straight chain sugar alcohol does not form crystals during dehydration". PCT No WO 96/05809 "Improved method for stabilisation of biological substances during drying and subsequent storage and compositions thereof", by Colaco C., Roser B.J. and Sen S. claims methods wherein even reducing sugars are used to stabilise products. This is achieved by preventing the sugars from attacking the product by using Maillard reaction inhibitors. This application states that mannitol has no stabilising effect whatsoever.

We have now found this to be incorrect. In contradiction to the statements in these documents we have found that certain monosaccharide sugar alcohols such as mannitol and inositol can be excellent stabilisers when correctly formulated and in fact have significant advantages over trehalose for some applications. In view of mannitol's acceptance by regulatory authorities and widespread use in the healthcare industry in both parenteral and oral formulations, it has considerable advantages as a new stabilising excipient. Its low cost and chemical inertness, together with its exceptional stability and

[illegible]

its high purity and safety, would make it the stabiliser of choice for pharmaceuticals. We have found that certain substances must be present in a formulation to convert mannitol into an excellent stabiliser. The effect of these substances is dose dependent and below a threshold concentration they do not work. The substances useful in accordance with this invention promote the drying of mannitol solutions as glasses rather than crystals. One of the most potent materials is the borate ion either as boric acid, or tetraborate salts of sodium or potassium. This probably forms a network complex with mannitol or even a covalent compound, sodium mannitoborate. Subsequent to the filing of this application containing the disclosure of the surprising efficacy of small amounts of borate in inducing glass formation in drying mannitol solutions, similar beneficial effects with borate and trehalose were reported by Miller et al. Notably, the molar ratio of borate to trehalose used by these authors was considerably higher than we found to be necessary. (Miller DP, Anderson RE and de Pablo JJ. Stabilisation of lactate dehydrogenase following freeze-thawing and vacuum-drying in the presence of trehalose and borate. *Pharmaceutical Research* 15 1215-1221 (1998)). Other effective materials such as calcium lactate, and proteins such as serum albumin or gelatin, or polyamine materials such as polyvinyl pyrrolidone, or polyvinyl alcohol, intrinsically form glasses themselves when dried from solution. Yet other effective chemicals such as acetate salts, will form glasses but only when quenched from the melt and only when the melt contains several metal cations rather than a single cation, such as sodium and calcium. An additional property of the materials identified to date is that the beneficial actions of these materials are additive so that they can be mixed together in successful formulations which contain sub-threshold doses of each additive alone. Other substances which are either themselves glass-formers (under certain conditions) or are glass-formation-facilitators such as the phosphate salts of sodium and potassium and sodium silicate are capable of being utilised to make stabilising glasses according to this invention.

The quality of the glasses made by this process is high. The glass transition temperature (T<sub>g</sub>) of 1:1 w/w mannitol/calcium lactate glass is around 68°C (Figure 1). This compares with a T<sub>g</sub> of around 90°C for a trehalose/sodium sulphate glass dried under the same conditions (Figure 2). Both types of glass have T<sub>g</sub>'s well above any possible ambient storage temperature and, because the glasses are chemically inert and non-reactive, the entrapped products are stable at room temperatures and require no refrigeration of any kind.

What is required is a robust formulation that inherently forms a good glass even in the absence of product but which can accommodate a wide range of product concentrations without loss of glass forming capacity and stabilising efficacy. A number of sugar alcohols previously rejected as stabilising agents in the prior art listed above such as mannitol, xylitol, inositol, arabinitol and galactitol stabilise very effectively when correctly formulated so as to promote the formation of a glassy matrix, rather than crystals, on drying. A simple method for inhibiting crystallisation is to mix two or more sugars or sugar derivatives together in the same formulation. When correctly chosen, these mutually inhibit crystallisation and the mixture dries as an amorphous glass. In some cases these glasses are more robust on storage and give greater stability to an included product than trehalose itself.

### Brief Description of the Figures

Figure 1 shows differential scanning calorimetry of a 50 / 50 w/w mannitol / calcium lactate glass showing a clear glass transition at a temperature of 68 °C;

Figure 2 shows differential scanning calorimetry of a 50 / 50 w/w trehalose / calcium lactate glass showing a clear glass transition at a temperature of 90 °C;

Figure 3 shows the percentage recovery of alkaline phosphatase activity after vacuum-drying in either trehalose or formula 7 containing mannitol, inositol, galactitol and degraded gelatin (Byco C) followed by storage at 37°C or 50°C for up to 6 weeks. There is no loss with formula 7 but serious losses with trehalose;

Figure 4 shows the percentage recovery of alkaline phosphatase activity after freeze-drying in either trehalose or formula 7 containing mannitol, inositol, galactitol and degraded gelatin (Byco C) followed by storage at 37°C or 50°C for up to 7 weeks. There is little loss with either stabiliser;

Figure 5 shows the percentage recovery of Erythropoietin (EPO) after vacuum-drying in either trehalose or formula 8 containing mannitol, inositol, galactitol and calcium lactate followed by storage at 37°C or 50°C for up to 6 weeks. While there is serious losses with trehalose, no loss occurs with formula 8; and

Figure 6 shows the percentage recovery of EPO after freeze-drying in either trehalose or formula 7 containing mannitol, Inositol, galactitol and degraded gelatin (Byco C) or formula 8 in which calcium lactate was substituted for the gelatin. After storage at 37°C or 50°C for 7 weeks, there is no loss with any of the stabilising formulations.

Figure 7 shows the percentage recovery of alkaline phosphatase activity after spray drying formula 9 to which had been added insoluble calcium phosphate powder to increase the density of the glass microspheres. After storage at either 37°C or 55°C for up to 90 days there was no significant loss of activity.

Figure 8 shows the percentage recovery alkaline phosphatase activity after spray drying formula 11 to which had been added insoluble barium sulphate powder to increase the density of the glass microspheres. After storage at either 37°C or 55°C for up to 90 days there was again no significant loss of activity.

## Examples

### Example 1

A solution of mannitol in water 20% w/v was pipetted in 100  $\mu$ l volumes on to the surface of clean glass microscope slides which were laid flat on a hotplate at 70°C for drying. Within about 5 min. the solution had dried into a mass of crystals. A 20% solution of trehalose or palatinit, dried under the same conditions formed a hard and transparent perfect glass film. Only the latter sugars stabilise actives successfully as described in the patents and publications referenced above. This is considered to be a function of their ability to form amorphous glass on drying.

The addition of a network forming additive such as sodium or potassium tetraborate to the mannitol solution in amounts of less than 10% of the weight of mannitol, completely inhibited crystallisation on drying and resulted in the formation of glasses as perfect as those made with trehalose or palatinit. This demonstrated that mannitol can form glasses under appropriate conditions and a search was then made for less toxic additives to achieve the same effect.

### Example 2

Equal weights of trehalose or palatinit were mixed with the mannitol in solution and dried as above. In both cases this yielded perfect glasses showing that these two glass-forming sugars could inhibit the crystallisation of mannitol. Even a sugar which was not itself a glass former, such as galactitol, inhibited the crystallisation of a mannitol / inositol mixture which itself crystallised readily. Similar results were found when equal weights of other glass forming substances such as calcium lactate, albumin, polyvinyl pyrrolidone or degraded gelatin (Byco C) were added to mannitol in solution. To establish the longer term stability of these glasses they were held at 70°C overnight and then at room temperature and ambient humidity for several weeks and inspected frequently. All the above glasses were stable under both sets of conditions. When other monosaccharide alcohols such as galactitol, xylitol, arabinitol, adonitol, or inositol were substituted for

mannitol, similar results were obtained but the resulting glasses were very soft when alcohols of the pentose sugars were used.

### Example 3

More complex mixtures of the monosaccharide alcohols could also be blended together with glass forming substances to yield excellent glasses, which showed good physical stability in the glass phase at 70°C and at ambient conditions for many weeks as described in Example 2. Some good formulations are:-

1. mannitol 33.3%, inositol 33.3% and PVP 33.3%
2. mannitol 31.6%, inositol 31.6% xylitol 5% and calcium lactate 31.6%
3. mannitol 33.3%, inositol 33.3% and calcium lactate 33.3%
4. mannitol 33.3%, inositol 33.3% and Byco C 33.3%
5. mannitol 23.3%, inositol 23.3% calcium lactate 30% and PVP 23.3%
6. mannitol 33.3%, arabinitol 33.3% and calcium lactate 33.3%
7. mannitol 30%, inositol 15% galactitol 15% and Byco C 40%
8. mannitol 30%, inositol 15% galactitol 15% and calcium lactate 40%
9. mannitol 33%, Byco C 33% and calcium lactate 33%
10. mannitol 50%, and Kollidon 30 (polyvinylpyrrolidone (PVP)) 50%
11. mannitol 33%, Kollidon 30 (polyvinylpyrrolidone (PVP)) 33% and calcium lactate 33%
12. mannitol 50%, and Dextran 50%
13. mannitol 33%, Dextran 33% and calcium lactate 33%

In short, simple trial and error experimentation will establish a successful formulation from mixtures of monosaccharide alcohols and a glass forming substance. By this method the final concentration of any single ingredient can be kept low. In this way a substantial total solids content can be achieved, even including sugar alcohols, which are individually not very soluble. The high solids content shortens drying times and increases the protection of the active during drying.

In addition to heat-assisted air-drying as above, formulations of this kind have been successfully vacuum dried, spray dried and freeze-dried.



#### Example 4

##### Stability of alkaline phosphatase enzyme.

Affinity purified alkaline phosphatase from bovine intestinal mucosa (Sigma Chemical Co cat No. p-8647) was vacuum-dried or freeze-dried in 200 µl volumes in formulation Number 7 above or in trehalose, and stored at 37°C or 50°C for 5 weeks. Samples were tested for activity at intervals using the Sigma assay with p-nitrophenyl phosphate as substrate. Vacuum drying was done at a shelf temperature of 40°C and a vacuum of 30-100 millitorr for 4 hr. The temperature was then ramped gradually to 60°C over 1 hr and the vials were stoppered and removed from the vacuum chamber for high temperature storage trials. Freeze-drying was done in a Labconco dryer at an initial shelf temperature of -40°C for 3 hr at a vacuum of 30-100 millitorr. The shelf temperature was then ramped to 0°C at 5°C / min and held for 1 hr. The shelf temperature was then raised to 40°C at 5°C / min and secondary drying was continued for a further 3 hr when the vials were stoppered under vacuum and removed for storage trials.

While there was some variability in the assays of enzyme activity, obvious trends were observed. Samples dried by either method without stabilisers lost all activity within a day or two of storage (not shown). Samples dried in either mannitol alone or a modified formula 7 lacking the glass forming facilitator lost between 75 and 80% of activity within 3 days at 37°C.

There was also a progressive loss of enzyme activity seen with the samples vacuum-dried in trehalose, which was not seen in the samples dried in formula 7 (Fig 3). This was particularly marked where the samples had been stored at the higher temperature (50°C). No such loss in the trehalose-dried samples was seen in the freeze-drying experiments where trehalose appeared to be slightly superior to the monosaccharide alcohols (Fig 4). This result might possibly indicate that a higher residual moisture content may have been responsible for the serious losses with trehalose in the vacuum dried samples. Whatever the explanation, it is clear that formula 7 gives results which are equivalent to, or superior to, the results obtained with trehalose.

### Example 5

### Stability of recombinant human Erythropoietin (EPO)

EPO was vacuum dried or freeze-dried as above in the same solutions and also in a variant of formulation 7 in which calcium lactate was substituted for Byco C (Formula 8), and then subjected to the same stability tests before being assayed by a standard 2-site sandwich Enzyme Immunoassay.

The results again showed a serious, progressive deterioration in the vacuum dried samples dried in trehalose, more dramatic at 50°C storage temperature, which was not seen with the samples dried in formula 8 (fig 5). The deterioration in trehalose was not seen in the freeze-dried samples stored at 37°C (not shown) or 50°C (Fig 6). Irrespective of whether formula 7 or 8 was used, all samples showed essentially complete recovery of activity.

### Example 6

The fluorescent protein R-Phycoerythrin was air-dried in trehalose, formula 3 or formula 4 on a hotplate as described in Example 1. The intensity of fluorescence was gauged visually when illuminated with a UV lamp. In the controls dried in trehalose fluorescence was retained. The material dried in formula 3 was masked by an intense silver autofluorescence from the Byco C while the material dried in formula 4 fluoresced with the characteristic orange colour with apparently undiminished intensity.

[illegible]